

## Chesterton 630 SXCF Synthetic, Extreme Pressure & Corrosion Resistant Grease

Category : Fluid , Lubricant

### Material Notes:

**Description:** Superior resistance to washout by water, caustics, sanitizing cleaners, process fluids and steam has now been combined with high temperature performance to product Chesterton® 630 SXCF. As a premium quality, water, corrosion and pressure resistant grease, 630 will not be removed even in severe water washout situations. With a dropping point at 318°C (604°F), it will not melt and run out. 630 SXCF is NSF Registered and complies with FDA regulations 178.3570. It can be the exclusive lubricating grease used in food, beverage, meat, poultry and pharmaceutical plants. Chesterton 630 SXCF is virtually non-staining. Grease stains on floors and packaging equipment can be substantially reduced. Use 630 to lubricate packaging machinery and paper converting equipment to virtually eliminate quality control rejects due to grease staining. Chesterton 630 SXCF is essentially tasteless and odorless. It is ideal as a maintenance or production lubricant used in food processing equipment, missing, filling, packaging and production machinery. Chesterton 630 SXCF contains no animal fats or oils which could become rancid and support biological growth. Further, it contains no heavy metals which could mandate hazardous warnings and restricts use. **Features:** Virtually impervious to water and steam Synthetic Base Fluid Smooth, Buttery Texture Adheres to Metal NSF H1 - Registration number 138415 FDA Compliant Virtually Tasteless and Odorless Speed Factor, Dn to 800,000 **Suggested Uses:** Use in all applications where conventional greases break down under shear, thermal abuse, shock loading and water contamination. Chesterton 630 SXCF can be used whenever thermally stable grease is required. **Applications:** Lubrication of slides, guides, plain bearings and bushings All types of anti-friction bearings, roller bearings and ball bearings Grease-lubricated chains Gears and cams Motor Operated Valves Couplings, joints and splined shafts And other moving parts of equipment used in the manufacture of food, drugs, cosmetics, beverages such as: Bottle and carton filling, Paste and sauce fillers, Conveyer belts and rollers, Feeders, mixers and agitators and Canning machines, seamers **Lubricating Additives:** Non Heavy Metal, Extreme Pressure and Anti-Wear, Anti-Fretting Additives, Surface Reactive Anti-Rust and Corrosion Additives, Oxidation Inhibitors **Information provided by Chesterton**

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Chesterton-630-SXCF-Synthetic-Extreme-Pressure-Corrosion-Resistant-Grease.php](http://www.lookpolymers.com/polymer_Chesterton-630-SXCF-Synthetic-Extreme-Pressure-Corrosion-Resistant-Grease.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.950 - 1.05 g/cc	0.950 - 1.05 g/cc	
Viscosity Measurement	145	145	Base Oil; ASTM D445
Kinematic Viscosity at 40°C (104°F)	50 cSt	50 cSt	Base Oil; ASTM D445
Kinematic Viscosity at 100°C (212°F)	8.5 cSt	8.5 cSt	Base Oil; ASTM D445

Mechanical Properties	Metric	English	Comments
Four Ball Extreme Pressure, Load Wear Index	92	92	ASTM D2596, DIN 51 350/4
Four Ball Extreme Pressure, Weld Load	620 kg	1370 lb (mass)	ASTM D2596, DIN 51 350/4
Four Ball Wear	0.420 mm	0.0165 in	1200 rpm, 40 kg, scar diameter; ASTM

Mechanical Properties	Metric @Temperature 75.0 °C, Time 3600 sec	English @Temperature 167 °F, Time 1.00 hour	D2266, DIN 51 350/5 Comments
Penetration	265 - 295	265 - 295	ASTM D217, DIN ISO 2137
Oil Separation	0.10 %	0.10 %	loss; ASTM D1742
Timken Test	27200 g	60.0 lb	ASTM D2509

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	240 °C	464 °F	
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	
Dropping Point	318 °C	604 °F	ASTM D2265, DIN 51 801/1

Descriptive Properties	Value	Comments
Bearing Life	280 hrs	ASTM D3527
Bomb Oxidation	4 psi drop	1000 hrs, ASTM D942
Color	Light Tan	
Consistency	2	NLGI, DIN 51 818
Copper Corrosion	0/1B	ASTM D4048, DIN 51 811
Corrosion Resistance	>1000 hrs	@ 50 microns film thickness, 5% NaCl, ASTM B117
Oil Base	USP White, Food Grade, PAO Synthetic	
Texture	Smooth, Buttery	
Thickener	Proprietary, Non-Melting, Sulfonate Complex	
Water Washout Resistance	<0.05%	@79°C, ASTM D1264
Worked Stability	-0.01	10000 Strokes, ASTM D217
	-0.028	10000 Strokes, ASTM D217

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China