

## ChevronTexaco Black Pearl® NLGI 1 Grease EP

Category : Fluid , Lubricant , Urea Gellant

### Material Notes:

**Features**Chevron Black Pearl Greases EP are multipurpose, extreme pressure, water-resistant greases.They are formulated with ISOSYN® base stock, a polyurea thickener, and rust and oxidation inhibitors. They are black in color and smooth and buttery in texture.**Applications**Chevron Black Pearl Greases EP provide outstanding film strength and adhesive properties. As a result, these products are particularly effective in providing superior wear protection in heavily loaded and shock load conditions.Chevron Black Pearl Greases EP stay in place, sticking to bearing surfaces and, thus, provide excellent lubrication under a wide range of operating conditions. They perform particularly well in roller bearings. These products provide exceptional water wash out results. They perform well in applications where cascading water or actual bearing submergence can occur. The rust inhibitors effectively protect bearing surfaces against corrosion. Pumpability is excellent over a wide range of temperatures as indicated by the Lincoln ventmeter test and the relatively low pressure drop in piping. Oxidation inhibitors ensure long life in storage and in use. In addition, Chevron Black Pearl Greases EP also perform well at high temperatures.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ChevronTexaco-Black-Pearl-NLGI-1-Grease-EP.php](http://www.lookpolymers.com/polymer_ChevronTexaco-Black-Pearl-NLGI-1-Grease-EP.php)

Physical Properties	Metric	English	Comments
Viscosity Measurement	94	94	Viscosity Index; ASTM D2270
Saybolt Viscosity at 100°F	671 SUS	671 SUS	
Saybolt Viscosity at 210°F	72 SUS	72 SUS	
Kinematic Viscosity at 40°C (104°F)	128 cSt	128 cSt	ASTM D445
Kinematic Viscosity at 100°C (212°F)	13 cSt	13 cSt	ASTM D445

Mechanical Properties	Metric	English	Comments
Four Ball Extreme Pressure, Weld Load	400 kg	882 lb (mass)	Weld Point
Four Ball Wear	0.420 mm	0.0165 in	
Penetration	325	325	Worked (60 strokes)
	370	370	Worked (100,000 strokes)
Penetration P(0), 1/10 mm	320	320	
Timken Test	27200 g	60.0 lb	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	149 °C	300 °F	

Minimum Service Temperature, Air Thermal Properties	-30.0 °C Metric	-22.0 °F English	Comments
Pour Point	-15.0 °C	5.00 °F	ASTM D97
Flash Point	246 °C	475 °F	ASTM D92
Dropping Point	245 °C	473 °F	

Descriptive Properties	Value	Comments
Bearing Rust	Pass	
Color	Black	
Corrosion, Copper Strip Test 3h	1a	
Lincoln Ventmeter, psig at 30 s, at 0°F	280	
Lincoln Ventmeter, psig at 30 s, at -22°F	625	
Lincoln Ventmeter, psig at 30 s, at 30°F	235	
Lincoln Ventmeter, psig at 30 s, at 75°F	215	
Texture	Smooth, Buttery	
Thickener, % / type	15.3 / Polyurea Complex	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China