

ChevronTexaco Rykon® 1364 Premium Grease

Category : Fluid , Lubricant , Urea Gellant

Material Notes:

FeaturesChevron Rykon Premium Grease No. 1364 contains polyurea thickener in highly refined paraffinic oil, as well as extreme pressure and rust protection additives. Chevron Rykon Premium Grease No. 1364:is resistant to oil separation during use and storage. has excellent high temperature characteristics.will not blacken copper or steel when tested for one hour at 150°C (302°F).**Applications**Chevron Rykon Premium Grease No. 1364 was formulated specifically for the automotive constant velocity (CV) driveline joints used in front-wheel drive automobiles.It is compatible with the common elastomers used for boots in the joints and can be used in "hot" CV joints up to 177°C (350°F).Chevron Rykon Premium Grease No. 1364 can also be used in other applications requiring a high temperature grease with extreme pressure additives.Chevron Rykon Premium Grease No. 1364 meets the requirements of GKN specification M-3005 for CV grease.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ChevronTexaco-Rykon-1364-Premium-Grease.php

Physical Properties	Metric	English	Comments
Viscosity Measurement	90	90	Viscosity Index of base oil; ASTM D2270
Saybolt Viscosity at 100°F	596 SUS	596 SUS	
Saybolt Viscosity at 210°F	76 SUS	76 SUS	
Kinematic Viscosity at 40°C (104°F)	115 cSt	115 cSt	ASTM D445
Kinematic Viscosity at 100°C (212°F)	14.1 cSt	14.1 cSt	ASTM D445

Mechanical Properties	Metric	English	Comments
Penetration	312	312	Worked
Timken Test	18100 g	40.0 lb	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	177 °C	351 °F	
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	
Dropping Point	243 °C	469 °F	

Descriptive Properties	Value	Comments
Bearing Rust	Pass	
Color	Blue	
Texture	Smooth	

Thickener 5 / tunc Descriptive Properties	10 / Polyurea Value	Comments
--	------------------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China