

ChevronTexaco Tool Joint Compound

Category : Fluid , Lubricant , Aluminum Gellant

Material Notes:

Features Chevron Tool Joint Compound is an aluminum complex grease designed principally for the lubrication of drill collars, tool joints and pipe threads. It contains copper flake and graphite, fortified with extreme pressure and antiwear additives. Chevron Tool Joint Compound: provides high antiweld protection and withstands high pressures stays on threads under severe torquing action protects the shoulders and thread faces of the tool joint against damage from galling or seizure during makeup or disassembly provides excellent corrosion, oxidation resistance provides good brushability at low temperatures. Chevron Tool Joint Compound is waterproof and highly resistant to washoff by water or drilling mud. Applications Chevron Tool Joint Compound is the preferred recommendation for the threads and shoulders of rotary shouldered tool joints and the entire drill string in most drilling applications.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ChevronTexaco-Tool-Joint-Compound.php

Physical Properties	Metric	English	Comments
Viscosity Measurement	64	64	Viscosity Index; ASTM D2270
Saybolt Viscosity at 100°F	560 SUS	560 SUS	
Saybolt Viscosity at 210°F	60 SUS	60 SUS	
Kinematic Viscosity at 40°C (104°F)	106 cSt	106 cSt	ASTM D445
Kinematic Viscosity at 100°C (212°F)	10 cSt	10 cSt	ASTM D445

Mechanical Properties	Metric	English	Comments
Penetration	315	315	Worked (60 strokes)

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	149 °C	300 °F	
Minimum Service Temperature, Air	-12.0 °C	10.4 °F	
Flash Point	221 °C	430 °F	ASTM D92
Dropping Point	232 °C	450 °F	

Descriptive Properties	Value	Comments
Color	Brown	
Texture	Buttery	
Thickener, % / type	- / Aluminum Complex	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China