

## Chi Mei Kibiton® PB-5502 Styrene-Butadiene Copolymer

Category : Polymer , Adhesive

**Material Notes:**

Hot melt adhesive

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Chi-Mei-Kibiton-PB-5502-Styrene-Butadiene-Copolymer.php](http://www.lookpolymers.com/polymer_Chi-Mei-Kibiton-PB-5502-Styrene-Butadiene-Copolymer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.940 g/cc	0.940 g/cc	ASTM D792
Volatiles	<= 0.60 %	<= 0.60 %	ASTM D1416
Melt Flow	8.5 g/10 min @Load 2.16 kg, Temperature 190 °C	8.5 g/10 min @Load 4.76 lb, Temperature 374 °F	
Ash	<= 0.20 %	<= 0.20 %	ASTM D1416

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	82	82	ASTM D2240

Descriptive Properties	Value	Comments
BD/SM %	64/36	
Oil Content (phr)	0	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China