

## China-Yixing Longly Refractories ASM-120 Cordierite-Mullite

Category : Ceramic , Oxide , Aluminum Oxide , Magnesium Oxide , Silicon Oxide

### Material Notes:

Featured mullite, cordierite as the main raw material, the use of advanced production technology, professionally manufacturing the kiln furniture of ceramic and powder metallurgy with load bearing board, shelf, seggar, slides, plate, pillars such as high-grade kiln tools. Refractoriness higher than its cordierite, thermal stability is better than corundum mullite material. Coefficient of thermal expansion of small, good thermal shock resistance and long service life, not sudden fracture; No oxidation in the process of use, no chipping, and less pollution ceramics. Mullite - cordierite kiln furniture is better material in 1300°C following firing ceramics. In the firing of ceramics, sanitary ceramics, furnishings ceramics, mosaic glaze, western-style brick, square brick, split bricks and glass-ceramics have had excellent results. Can be used for the tunnel kiln, shuttle kiln, belt kiln putting furnace and low-temperature-fired glaze or burn, the powder metallurgy heat treatment. Application: The kiln furniture of ceramic and powder metallurgy with load bearing board, shelf, seggar, plate such as high-grade kiln tools. Information Provided by China Yixing Longly Refractories Co. Ltd

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_China-Yixing-Longly-Refractories-ASM-120-Cordierite-Mullite.php](http://www.lookpolymers.com/polymer_China-Yixing-Longly-Refractories-ASM-120-Cordierite-Mullite.php)

Physical Properties	Metric	English	Comments
Bulk Density	>= 1.90 g/cc	>= 0.0686 lb/in <sup>3</sup>	
Porosity	<= 23 %	<= 23 %	Apparent

Mechanical Properties	Metric	English	Comments
Flexural Strength	>= 18.0 MPa	>= 2610 psi	high temp bending
	>= 50.0 MPa	>= 7250 psi	cold bending
Compressive Strength	>= 35.0 MPa	>= 5080 psi	Ambient

Thermal Properties	Metric	English	Comments
CTE, linear	4.20 μm/m-°C	2.33 μin/in-°F	Volumetric thermal expansion
Thermal Conductivity	1.60 W/m-K	11.1 BTU-in/hr-ft <sup>2</sup> -°F	
Maximum Service Temperature, Air	>= 1250 °C	>= 2280 °F	

Component Elements Properties	Metric	English	Comments
Al <sub>2</sub> O <sub>3</sub>	>= 36 %	>= 36 %	
MgO	>= 7.0 %	>= 7.0 %	
SiO <sub>2</sub>	<= 52 %	<= 52 %	

Descriptive Properties	Value	Comments
Refractoriness (°C)	>1200	Under load temperature, 0.2 MPa, 0.6%
Thermal Shock Resistance Times	30	1100°C water cooling

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China