

Chosun Refractories APC-120G Acid-proof Castable

Category : Ceramic , Oxide , Silicon Oxide

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-APC-120G-Acid-proof-Castable.php

Mechanical Properties	Metric	English	Comments
Modulus of Rupture	0.002943 GPa	0.4269 ksi	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	0.006867 GPa	0.9960 ksi	
	@Temperature 500 °C, Time 10800 sec	@Temperature 932 °F, Time 3.00 hour	
	0.00981 GPa	1.42 ksi	
	@Temperature 1000 °C, Time 10800 sec	@Temperature 1830 °F, Time 3.00 hour	
Compressive Strength	7.85 MPa	1140 psi	Cold Crushing Strength
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	24.5 MPa	3560 psi	Cold Crushing Strength
	@Temperature 500 °C, Time 10800 sec	@Temperature 932 °F, Time 3.00 hour	
	29.4 MPa	4270 psi	Cold Crushing Strength
	@Temperature 1000 °C, Time 10800 sec	@Temperature 1830 °F, Time 3.00 hour	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	1200 °C	2190 °F	limited
Shrinkage	-0.600 %	-0.600 %	
	@Temperature 1000 °C, Time 10800 sec	@Temperature 1830 °F, Time 3.00 hour	
	-0.400 %	-0.400 %	
	@Temperature 500 °C, Time 10800 sec	@Temperature 932 °F, Time 3.00 hour	
	-0.100 %	-0.100 %	
	@Temperature 110 °C,	@Temperature 230 °F,	

Thermal Properties	Time 86400 sec Metric	Time 24.0 hour English	Comments
--------------------	--------------------------	---------------------------	----------

Component Elements Properties	Metric	English	Comments
-------------------------------	--------	---------	----------

Al2O3	42 %	42 %	
SiO2	53 %	53 %	

Descriptive Properties	Value	Comments
------------------------	-------	----------

Installation Method	Spray	
---------------------	-------	--

Main Applications	Chemical Plant	
-------------------	----------------	--

Material Required for Estimating (kg/?)	2,200	
---	-------	--

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China