

Chosun Refractories AU1 Blast Furnace Runner Refractory

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-AU1-Blast-Furnace-Runner-Refractory.php

Physical Properties	Metric	English	Comments
Bulk Density	2.75 g/cc	0.0994 lb/in ³	
	@Temperature 1450 °C, Time 7200 sec	@Temperature 2640 °F, Time 2.00 hour	
	2.80 g/cc	0.101 lb/in ³	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
Porosity	17.3 %	17.3 %	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	27.5 %	27.5 %	
	@Temperature 1450 °C, Time 7200 sec	@Temperature 2640 °F, Time 2.00 hour	

Mechanical Properties	Metric	English	Comments
Modulus of Rupture	0.0024525 GPa	0.35571 ksi	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	0.0067689 GPa	0.98176 ksi	
	@Temperature 1450 °C, Time 10800 sec	@Temperature 2640 °F, Time 3.00 hour	
Compressive Strength	10.3 MPa	1490 psi	Cold Crushing Strength
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	27.6 MPa	4000 psi	Cold Crushing Strength
	@Temperature 1450 °C, Time 7200 sec	@Temperature 2640 °F, Time 2.00 hour	

Thermal Properties	Metric	English	Comments
Shrinkage	-0.0500 %	-0.0500 %	

Thermal Properties	Metric @Temperature 1450 °C, Time 7200 sec	English @Temperature 2640 °F, Time 2.00 hour	Comments
--------------------	--	--	----------

Component Elements Properties	Metric	English	Comments
Al2O3	70 %	70 %	
SiC	15 %	15 %	
SiO2	4.0 %	4.0 %	

Descriptive Properties	Value	Comments
Chemical Analysis(%),FC	3	
Installation Method	Casing Vibrating	
Main Applications	Main runner Metal Zone	
Material Required for Estimating (kg/?)	2,800	
Water Required for Casting(%)	6.5	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China