

## Chosun Refractories B-7 Insulating Firebrick

Category : Ceramic

### Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Chosun-Refractories-B-7-Insulating-Firebrick.php](http://www.lookpolymers.com/polymer_Chosun-Refractories-B-7-Insulating-Firebrick.php)

Physical Properties	Metric	English	Comments
Bulk Density	$\geq 1.00 \text{ g/cc}$	$\geq 0.0361 \text{ lb/in}^3$	

Mechanical Properties	Metric	English	Comments
Compressive Strength	$\leq 2.94 \text{ MPa}$	$\leq 427 \text{ psi}$	Cold Crushing Strength

Thermal Properties	Metric	English	Comments
Thermal Conductivity	$\geq 0.3606 \text{ W/m-K}$ @Temperature 350 °C	$\geq 2.498 \text{ BTU-in/hr-ft}^2\text{-}^\circ\text{F}$ @Temperature 662 °F	

Descriptive Properties	Value	Comments
Temp.(?) Reheating Shrinkage less than 2.0%	1,500	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China