

Chosun Refractories N3-2 Fireclay brick

Category : Ceramic

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-N3-2-Fireclay-brick.php

Physical Properties	Metric	English	Comments
Bulk Density	2.10 g/cc	0.0759 lb/in ³	
Porosity	21 %	21 %	

Mechanical Properties	Metric	English	Comments
Compressive Strength	29.4 MPa	4270 psi	Cold Crushing Strength

Thermal Properties	Metric	English	Comments
CTE, linear	5.30 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	2.94 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	
	@Temperature 1000 °C	@Temperature 1830 °F	
Shrinkage	-0.500 - 0.50 %	-0.500 - 0.50 %	
	@Temperature 1350 °C, Time 7200 sec	@Temperature 2460 °F, Time 2.00 hour	

Component Elements Properties	Metric	English	Comments
Al2O3	33 %	33 %	
Fe2O3	2.0 %	2.0 %	

Descriptive Properties	Value	Comments
Refractories Under Load(2kg/?,T2?)	1,290	
Refractoriness (SK)	32=	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China