

Chosun Refractories TG-68 Monolithic Refractories for Ladle and Tundish

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-TG-68-Monolithic-Refractories-for-Ladle-and-Tundish.php

Mechanical Properties	Metric	English	Comments
Modulus of Rupture	0.003924 GPa	0.5691 ksi	
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	
Compressive Strength	9.81 MPa	1420 psi	Cold Crushing Strength
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	

Thermal Properties	Metric	English	Comments
Shrinkage	-0.350 %	-0.350 %	
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	
	-0.0500 %	-0.0500 %	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	

Component Elements Properties	Metric	English	Comments
Al2O3	65 %	65 %	
SiO2	27 %	27 %	

Descriptive Properties	Value	Comments
Installation Method	Gunning, Troweling	
Main Applications	Tundish Coating	
Material Required for Estimating (kg/?)	2,000	
Water Required for Casting(%)	NOZZLE Mixing	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China