

## Clariant Remafin PESP0006 High Density Polyethylene, 10% Glass Fiber

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Glass fiber Filled

### Material Notes:

Data provided by Clariant Masterbatches

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Clariant-Remafin-PESP0006-High-Density-Polyethylene-10-Glass-Fiber.php](http://www.lookpolymers.com/polymer_Clariant-Remafin-PESP0006-High-Density-Polyethylene-10-Glass-Fiber.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.01 g/cc	1.01 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	36.5 MPa	5300 psi	ASTM D638
Flexural Yield Strength	37.9 MPa	5500 psi	ASTM D790
Flexural Modulus	1.38 GPa	200 ksi	ASTM D790
Izod Impact, Notched	1.17 J/cm @Temperature 22.8 °C	2.20 ft-lb/in @Temperature 73.0 °F	ASTM D256

Processing Properties	Metric	English	Comments
Melt Temperature	191 - 249 °C	375 - 480 °F	
Mold Temperature	21.1 - 65.6 °C	70.0 - 150 °F	
Injection Pressure	4.96 - 8.27 MPa	720 - 1200 psi	Secondary
	8.27 - 13.8 MPa	1200 - 2000 psi	Initial
Back Pressure	0.345 - 1.72 MPa	50.0 - 250 psi	
Shot Size	30 - 80 %	30 - 80 %	
Screw Speed	20 - 100 rpm	20 - 100 rpm	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China