Colorite Polymers CS6038SR Wire and Cable Insulation Vinyl Compound

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

Material Notes:

Description: Colorite specialty wire and cable compounds feature low smoke properties, excellent flame retardance, low temperature flexibility, and resistance to abrasion and chemicals. All are available in UL and non-UL grades. In addition, the engineering-grade thermoplastic elastomers we offer can stand up to the most demanding applications . . . while providing the most desirable performance characteristics at a cost that's more affordable than "ordinary" elastomers. Typical Applications: Semi-rigid UL, T 60°CInformation provided by Colorite Polymers.

Order this product through the following link: http://www.lookpolymers.com/polymer_Colorite-Polymers-CS6038SR-Wire-and-Cable-Insulation-Vinyl-Compound.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|-----------|-----------|
| Specific Gravity | 1.38 g/cc | 1.38 g/cc | ASTM D792 |
| Loss On Ignition | 25 % | 25 % | ASTM 2863 |

| Mechanical Properties | Metric | English | Comments |
|----------------------------|----------|----------|--------------------|
| Hardness, Shore A | 95 | 95 | 10 sec; ASTM D2240 |
| Tensile Strength, Ultimate | 20.3 MPa | 2950 psi | ASTM D412 |
| Elongation at Break | 305 % | 305 % | ASTM D412 |

| Thermal Properties | Metric | English | Comments | |
|----------------------------------|----------|---------|-----------|--|
| Maximum Service Temperature, Air | 60.0 °C | 140 °F | | |
| Brittleness Temperature | -10.0 °C | 14.0 °F | ASTM D746 | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China