

## ConocoPhillips Hydroclear® 320 Multipurpose R&O Oil, AGMA Lubricant No. 6

Category : Fluid , Lubricant

**Material Notes:**

Description: Conoco Hydroclear Multipurpose R&O Oil is a rust- and oxidationinhibited industrial oil with ashless wear protection formulated from premium Conoco hydrocracked base stocks. Hydroclear Multipurpose R&O Oil is specially formulated with proprietary additive chemistry and is recommended for use in a variety of systems which require rust- and oxidation-inhibited oils. The added benefit of mild antiwear protection can significantly increase equipment life, particularly in these hardworking times. These applications include general oiling, air compressors, steam turbines, hydraulic systems, circulating oil systems, oil-filled couplings, centrifugal pumps and lightly loaded gearboxes. Hydroclear Multipurpose R&O Oil has been tested and formally approved by Cincinnati Milacron under specifications P-38 (ISO 32), P-55 (46) and P-54 (68). Hydroclear Multipurpose R&O Oil exceeds Vickers I-286-S requirements. Hydroclear Multipurpose R&O Oil 460 meets the requirements of the Morgoil Lubricant Specification for use in roll-neck bearings. Proven performance in turbines which require antiwear, such as ABB and Alstom (some). Excellent for mist lubrication systems. Information provided by ConocoPhillips.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ConocoPhillips-Hydroclear-320-Multipurpose-RO-Oil-AGMA-Lubricant-No-6.php](http://www.lookpolymers.com/polymer_ConocoPhillips-Hydroclear-320-Multipurpose-RO-Oil-AGMA-Lubricant-No-6.php)

Physical Properties	Metric	English	Comments
Density	0.888 g/cc	0.0321 lb/in <sup>3</sup>	
Viscosity Measurement	95	95	Viscosity Index
Saybolt Viscosity at 100°F	1694 SUS	1694 SUS	
Saybolt Viscosity at 210°F	119 SUS	119 SUS	
Kinematic Viscosity at 40°C (104°F)	318 cSt	318 cSt	
Kinematic Viscosity at 100°C (212°F)	23.9 cSt	23.9 cSt	
Oxidative Stability	3000 hour	3000 hour	
ASTM Color	5.0	5.0	

Mechanical Properties	Metric	English	Comments
Four Ball Wear	0.400 mm	0.0157 in	

Thermal Properties	Metric	English	Comments
Pour Point	-15.0 °C	5.00 °F	
Rotating Bomb Oxidation Test (RBOT)	600 min	600 min	ASTM D 2272
Flash Point	277 °C	530 °F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	30.0 kV/mm	762 kV/in	No thickness given

Descriptive Properties	Value	Comments
ASTM Rust A&B	Pass	
Copper Corrosion	1A	
Emulsion Characteristics (40-40-0)	25 minutes	
FZG	Pass 9 Load Stages	ASTM D5182

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China