

## ConocoPhillips Hydroclear® 350 Industrial Oil

Category : Fluid , Lubricant

### Material Notes:

Description: Conoco Hydroclear Industrial Oil is a high-quality, general-purpose industrial lubricant formulated from premium Conoco hydrocracked base stocks. Hydroclear Industrial Oil is recommended for use in a variety of applications which require a pure fluid.

Hydroclear Industrial Oil is ideally suited for use as a seal oil, process oil, concrete form oil, deepwell pump drip oil, diluent, extender oil or other similar application. Hydroclear Industrial Oil provides good thermal stability, low volatility and high purity. Hydroclear Industrial Oil is available in seven different viscosity grades to meet the needs of most applications and operating conditions. Information provided by ConocoPhillips.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ConocoPhillips-Hydroclear-350-Industrial-Oil.php](http://www.lookpolymers.com/polymer_ConocoPhillips-Hydroclear-350-Industrial-Oil.php)

Physical Properties	Metric	English	Comments
Density	0.866 g/cc	0.0313 lb/in <sup>3</sup>	
Viscosity Measurement	100	100	Viscosity Index
Saybolt Viscosity at 100°F	363 SUS	363 SUS	
Saybolt Viscosity at 210°F	56 SUS	56 SUS	
Kinematic Viscosity at 40°C (104°F)	70 cSt	70 cSt	
Kinematic Viscosity at 100°C (212°F)	9.1 cSt	9.1 cSt	
ASTM Color	0.50	0.50	

Thermal Properties	Metric	English	Comments
Pour Point	-15.0 °C	5.00 °F	
Flash Point	238 °C	460 °F	

Optical Properties	Metric	English	Comments
Refractive Index	1.45	1.45	

Descriptive Properties	Value	Comments
Aniline Point	248°F	
Carbon Residue	0.06	
Characterization D-2007	0.1% Polar	Test inaccurate with HC base oils
	3.3% Aromatics (fully saturated)	Test inaccurate with HC base oils

Descriptive Properties	95.5% Saturated Value	Comments
Composition, Supercritical Fluid Chromatography	0% Aromatics	Test inaccurate with HC base oils
	0% Polars	
	100% Saturates	
Distillation D-2887 10%	770	
Distillation D-2887 50%	889	
Distillation D-2887 90%	991	
Distillation D-2887 IBP	662	
HPLC Aromatic Detection 1-Ring	400 ppm	
HPLC Aromatic Detection 2.5-Ring	Max 1 ppm	
HPLC Aromatic Detection 2-Ring	1 ppm	
HPLC Aromatic Detection 3-Ring and Above	Not Detectable	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China