

CoorsTek CAP 3 99.5% Alumina Ceramic Armor Material

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

CoorsTek CeraShield™ ceramics provide: low weight, high hardness, controlled, uniform microstructure, dimensional stability over wide temperature range, compatibility for use in finished armor systems with proven ballistic performance for National Institute of Justice (N.I.J.) and international design standards(C).

Order this product through the following link:

http://www.lookpolymers.com/polymer_CoorsTek-CAP-3-995-Alumina-Ceramic-Armor-Material.php

Physical Properties	Metric	English	Comments
Density	3.90 g/cc	0.141 lb/in ³	ASTM-C 20

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell 45 N	83	83	
Modulus of Elasticity	370 GPa	53700 ksi	ASTM-C848
Flexural Strength	379 MPa	55000 psi	MOR; ASTM-F417
Compressive Strength	2600 MPa	377000 psi	ASTM-C773
Poissons Ratio	0.22	0.22	ASTM-C848
Fracture Toughness	4.00 - 5.00 MPa-m ^{1/2}	3.64 - 4.55 ksi-in ^{1/2}	KIc; Notched Beam
Shear Modulus	152 GPa	22000 ksi	Calculated

Thermal Properties	Metric	English	Comments
CTE, linear	8.20 μm/m-°C	4.56 μin/in-°F	ASTM-C372
	@Temperature 25.0 - 1000 °C	@Temperature 77.0 - 1830 °F	
Thermal Conductivity	30.0 W/m-K	208 BTU-in/hr-ft ² -°F	ASTM-C408

Component Elements Properties	Metric	English	Comments
Al2O3	99.5 %	99.5 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China