

Cosmic Plastics E4930 Mineral & Glass Filled Epoxy Molding Compound, Encapsulated Grade

Category : Polymer , Thermoset , Epoxy , Epoxy, Encapsulating, Glass or Mineral Filled , Filled/Reinforced Thermoset

Material Notes:

Data provided by the manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cosmic-Plastics-E4930-Mineral-Glass-Filled-Epoxy-Molding-Compound-Encapsulated-Grade.php

Physical Properties	Metric	English	Comments
Density	2.00 g/cc	0.0723 lb/in ³	
Apparent Bulk Density	0.800 g/cc	0.0289 lb/in ³	
Water Absorption	0.25 %	0.25 %	48 hrs, 50°C
Linear Mold Shrinkage	0.0010 - 0.0040 cm/cm	0.0010 - 0.0040 in/in	typical.

Mechanical Properties	Metric	English	Comments
Hardness, Barcol	65	65	
Tensile Strength, Ultimate	83.0 MPa	12000 psi	
Flexural Strength	103 MPa	14900 psi	
Flexural Modulus	14.0 GPa	2030 ksi	
Compressive Strength	193 MPa	28000 psi	
Izod Impact, Notched	0.320 J/cm	0.599 ft-lb/in	

Thermal Properties	Metric	English	Comments
CTE, linear	25.0 $\mu\text{m}/\text{m}\cdot\text{C}$	13.9 $\mu\text{in}/\text{in}\cdot\text{F}$	Alpha 1
	@Temperature 20.0 °C	@Temperature 68.0 °F	
CTE, linear, Transverse to Flow	80.0 $\mu\text{m}/\text{m}\cdot\text{C}$	44.4 $\mu\text{in}/\text{in}\cdot\text{F}$	Alpha 2
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Thermal Conductivity	1.2561 W/m-K	8.7173 BTU-in/hr-ft ² -°F	
Deflection Temperature at 1.8 MPa (264 psi)	≥ 200 °C	≥ 392 °F	
Glass Transition Temp, Tg	165 °C	329 °F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	
Dielectric Constant	4.2	4.2	Wet
	@Frequency 1000 Hz	@Frequency 1000 Hz	
Dielectric Constant	4.5	4.5	Wet
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	14.0 kV/mm	356 kV/in	Wet, Step by Step
Dissipation Factor	0.011	0.011	Wet
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dissipation Factor	0.012	0.012	Wet
	@Frequency 1000 Hz	@Frequency 1000 Hz	
Arc Resistance	180 sec	180 sec	

Processing Properties	Metric	English	Comments
Processing Temperature	150 - 175 °C	302 - 347 °F	Molding temperature

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China