

## Cossa Polimeri ESTABLEND PA 2516 GF ABS / Nylon 6 Blend, 8% Glass Filled

Category : Polymer , Thermoplastic , ABS Polymer , Nylon , Nylon 6

### Material Notes:

ESTABLEND PA is a blend of acrylonitrile butadiene styrene and polyamide 6.8% glass fiber reinforced. Exceptional chemical resistance, excellent heat resistance, good dimensional stability. Information provided by Cossa Polimeri S.r.l.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Cossa-Polimeri-ESTABLEND-PA-2516-GF-ABS-Nylon-6-Blend-8-Glass-Filled.php](http://www.lookpolymers.com/polymer_Cossa-Polimeri-ESTABLEND-PA-2516-GF-ABS-Nylon-6-Blend-8-Glass-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.12 g/cc	0.0405 lb/in <sup>3</sup>	ISO 1183
Linear Mold Shrinkage	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	ISO 2577
Melt Flow	27 g/10 min @Load 10.0 kg, Temperature 240 °C	27 g/10 min @Load 22.0 lb, Temperature 464 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	60.0 MPa	8700 psi	ISO 527
Elongation at Break	3.0 %	3.0 %	ISO 527
Tensile Modulus	3.70 GPa	537 ksi	ISO 527
Flexural Modulus	3.50 GPa	508 ksi	ISO 178
Izod Impact, Notched	0.0600 J/cm @Temperature 23.0 °C	0.112 ft-lb/in @Temperature 73.4 °F	ISO 180/A

Thermal Properties	Metric	English	Comments
Vicat Softening Point	115 °C @Load 5.00 kg	239 °F @Load 11.0 lb	50°C/hr; ISO 306
	190 °C @Load 0.999 kg	374 °F @Load 2.20 lb	50°C/hr; ISO 306
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	
	HB @Thickness 3.20 mm	HB @Thickness 0.126 in	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**