

Cossa Polimeri ESTABLEND PA 4016 GF ABS / Nylon 6 Blend, 8% Glass Filled

Category : Polymer , Thermoplastic , ABS Polymer , Nylon , Nylon 6

Material Notes:

ESTABLEND PA is a blend of acrylonitrile butadiene styrene and polyamide 6.8% glass fiber reinforced. Exceptional chemical resistance, excellent heat resistance, good dimensional stability. Information provided by Cossa Polimeri S.r.l.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cossa-Polimeri-ESTABLEND-PA-4016-GF-ABS-Nylon-6-Blend-8-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.10 g/cc	0.0397 lb/in ³	ISO 1183
Linear Mold Shrinkage	0.0030 - 0.0060 cm/cm	0.0030 - 0.0060 in/in	ISO 2577
Melt Flow	40 g/10 min @Load 10.0 kg, Temperature 240 °C	40 g/10 min @Load 22.0 lb, Temperature 464 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	60.0 MPa	8700 psi	ISO 527
Elongation at Break	5.0 %	5.0 %	ISO 527
Tensile Modulus	3.00 GPa	435 ksi	ISO 527
Flexural Modulus	2.60 GPa	377 ksi	ISO 178
Izod Impact, Notched	0.100 J/cm @Temperature 23.0 °C	0.187 ft-lb/in @Temperature 73.4 °F	ISO 180/A

Thermal Properties	Metric	English	Comments
Vicat Softening Point	135 °C @Load 5.00 kg	275 °F @Load 11.0 lb	50°C/hr; ISO 306
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	
	HB @Thickness 3.20 mm	HB @Thickness 0.126 in	

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China