

## Cossa Polimeri ESTADIENE 0460 GF Acrylonitrile Butadiene Styrene, 30% Glass Filled

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), 30% Glass Fiber Filled

### Material Notes:

ABS with 30% glass fiber reinforcementExcellent dimensional stability, low shrinkage, good impact resistanceInformation provided by Cossa Polimeri S.r.l.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Cossa-Polimeri-ESTADIENE-0460-GF-Acrylonitrile-Butadiene-Styrene-30-Glass-Filled.php](http://www.lookpolymers.com/polymer_Cossa-Polimeri-ESTADIENE-0460-GF-Acrylonitrile-Butadiene-Styrene-30-Glass-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.25 g/cc	0.0452 lb/in <sup>3</sup>	ASTM D 792
Linear Mold Shrinkage	0.0010 - 0.0030 cm/cm	0.0010 - 0.0030 in/in	ASTM D 955
Melt Flow	5.0 g/10 min @Load 10.0 kg, Temperature 220 °C	5.0 g/10 min @Load 22.0 lb, Temperature 428 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	70.0 MPa	10200 psi	ASTM D 638
Elongation at Break	1.6 %	1.6 %	ASTM D 638
Flexural Modulus	6.50 GPa	943 ksi	ASTM D 790
Izod Impact, Notched	0.600 J/cm @Temperature 0.000 °C	1.12 ft-lb/in @Temperature 32.0 °F	ASTM D 638
	0.700 J/cm @Temperature 23.0 °C	1.31 ft-lb/in @Temperature 73.4 °F	ASTM D 256

Thermal Properties	Metric	English	Comments
Vicat Softening Point	106 °C @Load 5.00 kg	223 °F @Load 11.0 lb	50°C/hr; ASTM D 1525
	115 °C @Load 0.999 kg	239 °F @Load 2.20 lb	50°C/hr; ASTM D 1525
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	
	HB	HB	

Thermal Properties	@Thickness 3.20 mm Metric	@Thickness 0.126 in English	Comments
Glow Wire Test	650 °C	1200 °F	I.E.C. 695-2-1
	@Thickness 2.00 mm	@Thickness 0.0787 in	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China