

Covestro Apec® HT KU 1-9354 High-Heat Polycarbonate

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, High Heat

Material Notes:

Only opaque colors available, flame retardant. Applications: Lighting, electrical parts. Information provided by Bayer. As of 1 September 2015, Bayer Material Science was separated from Bayer AG and officially adopted its new name – Covestro.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Covestro-Apec-HT-KU-1-9354-High-Heat-Polycarbonate.php

Physical Properties	Metric	English	Comments
Density	1.15 g/cc	0.0415 lb/in ³	
Water Absorption	0.40 %	0.40 %	Saturation in water
Moisture Absorption at Equilibrium	0.20 %	0.20 %	Equilibrium at 50% RH
Water Absorption at Saturation	0.40 %	0.40 %	
Melt Flow	8.0 g/10 min	8.0 g/10 min	
	@Load 2.16 kg, Temperature 330 °C	@Load 4.76 lb, Temperature 626 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	65.0 MPa	9430 psi	
Elongation at Break	50 %	50 %	Nominal
Elongation at Yield	7.0 %	7.0 %	
Tensile Modulus	2.30 GPa	334 ksi	
Charpy Impact Unnotched	NB	NB	
	0.800 J/cm ²	3.81 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.800 J/cm ²	3.81 ft-lb/in ²	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	70.0 µm/m-°C	38.9 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
CTE, linear, Transverse to Flow	70.0 µm/m-°C	38.9 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa	174 °C	345 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	162 °C	324 °F	
Vicat Softening Point	183 °C	361 °F	
Flammability, UL94	V-0	V-0	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	V-0	V-0	
	@Thickness 3.00 mm	@Thickness 0.118 in	
Oxygen Index	35 %	35 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	
Dielectric Constant	2.9	2.9	
	@Frequency 100 Hz	@Frequency 100 Hz	
	2.9	2.9	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	30.0 kV/mm	762 kV/in	
Dissipation Factor	0.0018	0.0018	
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.0080	0.0080	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	225 V	225 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China