

Covestro Bayflex® 110-80 Polyurethane Elastomeric RIM, MDI-based 2-Component Liquid System

Category : Polymer , Thermoset , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

Material Notes:

0.125 in. thickness. RIM = Reaction Injection Molding Information provided by Bayer Corporation, Polyurethanes Division As of 1 September 2015, Bayer Material Science was separated from Bayer AG and officially adopted its new name – Covestro.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Covestro-Bayflex-110-80-Polyurethane-Elastomeric-RIM-MDI-based-2-Component-Liquid-System.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.013 cm/cm	0.013 in/in	Bayer Test

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	24.0 MPa	3480 psi	ASTM D638/D412
Elongation at Break	135 %	135 %	ASTM D638/D412
Flexural Modulus	0.600 GPa	87.0 ksi	ASTM D790
Izod Impact, Notched	2.70 J/cm	5.06 ft-lb/in	ASTM D256
Tear Strength	82.0 kN/m	468 pli	Die C; ASTM D624

Thermal Properties	Metric	English	Comments
CTE, linear	110 µm/m-°C	61.1 µin/in-°F	ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Flammability, UL94	HB	HB	
	@Thickness 3.18 mm	@Thickness 0.125 in	
	HB	HB	
	@Thickness 3.18 mm	@Thickness 0.125 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China