

## Covestro Bayflex® XGT-100 Polyurethane Elastomeric RIM, 15% Milled Glass Filled, MDI-based 2-Component Liquid System

Category : Polymer , Thermoset , Filled/Reinforced Thermoset , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Glass Filled , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

0.125 in. thickness. RIM = Reaction Injection Molding Information provided by Bayer Corporation, Polyurethanes Division As of 1 September 2015, Bayer Material Science was separated from Bayer AG and officially adopted its new name – Covestro.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Covestro-Bayflex-XGT-100-Polyurethane-Elastomeric-RIM-15-Milled-Glass-Filled-MDI-based-2-Component-Liquid-System.php](http://www.lookpolymers.com/polymer_Covestro-Bayflex-XGT-100-Polyurethane-Elastomeric-RIM-15-Milled-Glass-Filled-MDI-based-2-Component-Liquid-System.php)

Physical Properties	Metric	English	Comments
Density	1.15 g/cc	0.0415 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage	0.0060 cm/cm	0.0060 in/in	Bayer Test

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	28.0 MPa	4060 psi	ASTM D638/D412
Elongation at Break	50 %	50 %	ASTM D638/D412
Flexural Modulus	1.47 GPa	213 ksi	ASTM D790
Izod Impact, Notched	2.10 J/cm	3.93 ft-lb/in	ASTM D256
Tear Strength	120 kN/m	685 pli	Die C; ASTM D624

Thermal Properties	Metric	English	Comments
CTE, linear	50.0 $\mu\text{m}/\text{m}\cdot\text{°C}$	27.8 $\mu\text{in}/\text{in}\cdot\text{°F}$	ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China