

Covestro Desmopan® 385 E Polyurethane

Category : Polymer , Thermoplastic , Polyurethane, TP

Material Notes:

Extrusion- and injection molding gradehigh mechanical strengthApplicationFilmsHosesnon-reinforcedScreenpacksTechnical partshard - soft systemsPreprocessingMax. Water content

Order this product through the following link:

http://www.lookpolymers.com/polymer_Covestro-Desmopan-385-E-Polyurethane.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	ISO 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	85	85	3s; ISO 868
Hardness, Shore D	32	32	15s; ISO 868
Abrasion	30	30	mm ³ ; ISO 4649
Compression Set	25 %	25 %	ISO 815
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	50 %	50 %	ISO 815
	@Temperature 70.0 °C	@Temperature 158 °F	

Descriptive Properties	Value	Comments
Availability	Asia Pacific	
	Europe	
	India	
	Near East/Africa	
	North America	
	South and Central America	
Feature	Release agent	
Form	Pellets	
Process	Film Extrusion	
	Injection Molding	
	Other Extrusion	

Descriptive Properties	Value	Comments
------------------------	-------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China