

Covestro Makrolon® 2858 Polycarbonate, Injection Grade

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Unreinforced, Flame Retardant

Material Notes:

Medium flowing BgVV- and FDA injection molding grade, for food contact applications, better resistance to hot water. Information provided by Bayer. As of 1 September 2015, Bayer MaterialScience was separated from Bayer AG and officially adopted its new name – Covestro.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Covestro-Makrolon-2858-Polycarbonate-Injection-Grade.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	
Water Absorption	0.35 %	0.35 %	Saturation in water
Moisture Absorption at Equilibrium	0.15 %	0.15 %	Equilibrium at 50% RH
Water Absorption at Saturation	0.35 %	0.35 %	
Linear Mold Shrinkage	0.0060 - 0.0080 cm/cm	0.0060 - 0.0080 in/in	ASTM D955
Melt Flow	9.5 g/10 min	9.5 g/10 min	
	@Load 1.20 kg, Temperature 300 °C	@Load 2.65 lb, Temperature 572 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	75	75	ASTM D785
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength, Ultimate	72.0 MPa	10400 psi	ASTM D638
Tensile Strength, Yield	63.0 MPa	9140 psi	
Elongation at Break	120 %	120 %	ASTM D638
Elongation at Yield	6.0 %	6.0 %	
Tensile Modulus	2.40 GPa	348 ksi	
Flexural Yield Strength	86.0 MPa	12500 psi	at 5% strain; ASTM D790
Flexural Modulus	2.30 GPa	334 ksi	ASTM D790
Izod Impact, Notched	9.10 J/cm	17.0 ft-lb/in	ASTM D256
	@Thickness 3.20 mm	@Thickness 0.126 in	
Charpy Impact Unnotched	NB	NB	
Tensile Creep Modulus, 1 hour			

Mechanical Properties	2200 MPa Metric	319000 psi English	Comments
Tensile Creep Modulus, 1000 hours	1900 MPa	276000 psi	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	70.0 $\mu\text{m}/\text{m}\cdot\text{C}$	38.9 $\mu\text{in}/\text{in}\cdot\text{F}$	
	@Temperature 20.0 $^{\circ}\text{C}$	@Temperature 68.0 $^{\circ}\text{F}$	
CTE, linear, Transverse to Flow	70.0 $\mu\text{m}/\text{m}\cdot\text{C}$	38.9 $\mu\text{in}/\text{in}\cdot\text{F}$	
	@Temperature 20.0 $^{\circ}\text{C}$	@Temperature 68.0 $^{\circ}\text{F}$	
Specific Heat Capacity	1.17 J/g- $^{\circ}\text{C}$	0.280 BTU/lb- $^{\circ}\text{F}$	ASTM D2766
Thermal Conductivity	0.200 W/m-K	1.39 BTU-in/hr-ft 2 - $^{\circ}\text{F}$	ASTM C177
Deflection Temperature at 0.46 MPa (66 psi)	136 $^{\circ}\text{C}$	277 $^{\circ}\text{F}$	
Deflection Temperature at 1.8 MPa (264 psi)	129 $^{\circ}\text{C}$	264 $^{\circ}\text{F}$	
Vicat Softening Point	145 $^{\circ}\text{C}$	293 $^{\circ}\text{F}$	
Glass Transition Temp, Tg	148 $^{\circ}\text{C}$	298 $^{\circ}\text{F}$	
UL RTI, Electrical	125 $^{\circ}\text{C}$	257 $^{\circ}\text{F}$	
	@Thickness 1.50 mm	@Thickness 0.0591 in	
UL RTI, Mechanical with Impact	115 $^{\circ}\text{C}$	239 $^{\circ}\text{F}$	
	@Thickness 1.50 mm	@Thickness 0.0591 in	
UL RTI, Mechanical without Impact	125 $^{\circ}\text{C}$	257 $^{\circ}\text{F}$	
	@Thickness 1.50 mm	@Thickness 0.0591 in	
Flammability, UL94	V-2	V-2	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	V-2	V-2	
	@Thickness 2.40 mm	@Thickness 0.0945 in	
Oxygen Index	26 %	26 %	

Optical Properties	Metric	English	Comments
Refractive Index	1.586	1.586	
Haze	1.0 %	1.0 %	ASTM D1003
	@Thickness 3.20 mm	@Thickness 0.126 in	

Optical Properties	Metric	English	Comments
	@Thickness 3.20 mm	@Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	
Dielectric Constant	2.9	2.9	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	3.0	3.0	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	30.0 kV/mm	762 kV/in	
Dissipation Factor	0.0010	0.0010	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dissipation Factor	0.010	0.010	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Arc Resistance	120 sec	120 sec	Tungsten Electrodes; ASTM D495
Comparative Tracking Index	275 V	275 V	
Hot Wire Ignition, HWI	30 - 60 sec	30 - 60 sec	UL Rating PLC 2 (30-60 sec)
	@Thickness 3.00 mm	@Thickness 0.118 in	
High Amp Arc Ignition, HAI	>= 120 arcs	>= 120 arcs	UL Rating PLC 0 (>120 arcs)
	@Thickness 1.50 mm	@Thickness 0.0591 in	
High Voltage Arc-Tracking Rate, HVTR	25.4 - 80.0 mm/min	1.00 - 3.15 in/min	UL Rating PLC 2 (25.4-80 mm/min.)
	@Thickness 1.50 mm	@Thickness 0.0591 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China