

## Cytec Thornel® Mat VME Carbon Fiber

Category : Carbon , Carbon Fiber , Other Engineering Material , Composite Fibers

**Material Notes:**

Data provided by the manufacturer, Amoco Performance Products, Inc. Form of mat VMA with shorter fibers for injection molding. Fiber lengths average 200 µm - inadequate for good mechanical property improvement but can result in improved shrinkage, thermal and electrical conductivity, and frictional characteristics. 98% carbon assay, 13 µm filament diameter Thornel® products were sold by Amoco and are now owned by Cytec.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Cytec-Thornel-Mat-VME-Carbon-Fiber.php](http://www.lookpolymers.com/polymer_Cytec-Thornel-Mat-VME-Carbon-Fiber.php)

Physical Properties	Metric	English	Comments
Density	2.00 g/cc	0.0723 lb/in <sup>3</sup>	Filament Property.
Apparent Bulk Density	0.600 g/cc	0.0217 lb/in <sup>3</sup>	
Specific Surface Area	0.40 m <sup>2</sup> /g	0.40 m <sup>2</sup> /g	Filament Property

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	1400 MPa	203000 psi	Filament Property. Mat strength is 120 N/m
Modulus of Elasticity	170 GPa	24700 ksi	Filament property, in tension

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.410 W/m-K	2.85 BTU-in/hr-ft <sup>2</sup> -°F	across thickness of mat

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00120 ohm-cm	0.00120 ohm-cm	Filament
	0.700 ohm-cm	0.700 ohm-cm	Mat

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China