

DSM Akulon® K222-KGMV14 Nylon 6-25% Glass and Mineral Reinforced (European Grade) (Cond)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Glass/Mineral Reinforced

Material Notes:

The Akulon® product portfolio is engineered for optimum performance to suit different processing techniques and end use markets. Akulon Nylon 6 is used for extrusion applications including barrier film, stock shapes, convoluted tubes, and monofilament. Akulon XP is a high-productivity, high-performance PA6 grade for film extrusion processes. Medium viscosity, unreinforced or reinforced Akulon grades are used for various injection molding and blow molding applications. Akulon® Ultraflow® is a high-productivity, high-performance PA6 family for molding processes. Key applications for Akulon: Automotive: Intake manifold, Engine, Powertrain, Airbag containers, Exterior trim, Interior trim, Electrical components and connectors Consumer durables: Power tools, Lawn and garden tools, Small appliances, Sports and leisure equipment, Furniture, Industrial Goods, Transportation E&E: Low voltage switch gear/power distribution, Lighting, Power connectors Film: Specialty and barrier films Information provided by DSM.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Akulon-K222-KGMV14-Nylon-6-25-Glass-and-Mineral-Reinforced-European-Grade-Cond.php

Physical Properties	Metric	English	Comments
Density	1.36 g/cc	0.0491 lb/in ³	(DAM); ISO 1183
Water Absorption	6.8 %	6.8 %	DAM; Sim. to ISO 62
Moisture Absorption at Equilibrium	2.0 %	2.0 %	Humidity Absorption (DAM); Sim. to ISO 62

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	45.0 MPa	6530 psi	ISO 527-1/-2
Elongation at Break	25 %	25 %	ISO 527-1/-2
Tensile Modulus	3.00 GPa	435 ksi	ISO 527-1/-2
Charpy Impact Unnotched	3.50 J/cm ²	16.7 ft-lb/in ²	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	5.00 J/cm ²	23.8 ft-lb/in ²	ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.400 J/cm ²	1.90 ft-lb/in ²	ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.800 J/cm ²	3.81 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	10°C/min (DAM); ISO 11357-1/-3
UL RTI, Electrical	65.0 °C	149 °F	UL746B
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	65.0 °C	149 °F	UL746B
	@Thickness 0.750 mm	@Thickness 0.0295 in	
UL RTI, Mechanical with Impact	65.0 °C	149 °F	UL746B
	@Thickness 0.750 mm	@Thickness 0.0295 in	
	65.0 °C	149 °F	UL746B
	@Thickness 1.50 mm	@Thickness 0.0591 in	
UL RTI, Mechanical without Impact	65.0 °C	149 °F	UL746B
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	65.0 °C	149 °F	UL746B
	@Thickness 0.750 mm	@Thickness 0.0295 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	IEC 60093
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	IEC 60093
Dielectric Constant	3.9	3.9	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	10	10	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	25.0 kV/mm	635 kV/in	IEC 60243-1
Dissipation Factor	0.10	0.10	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	0.30	0.30	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Comparative Tracking Index	475 V	475 V	IEC 60112

Descriptive Properties	Value	Comments
Flame Retardant	Yes	

Flame Retardant Agent Descriptive Properties	Yes Value	Comments
Heat stabilized or stable to heat	Yes	
Injection molding	Yes	
Release Agent	Yes	
With Fillers	Yes	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China