

DSM Akulon® K223-KMV6 (GREY) Nylon 6-30% Mineral Reinforced (European and Asian Grade) (Cond)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 30% Mineral Filled

Material Notes:

The Akulon® product portfolio is engineered for optimum performance to suit different processing techniques and end use markets. Akulon Nylon 6 is used for extrusion applications including barrier film, stock shapes, convoluted tubes, and monofilament. Akulon XP is a high-productivity, high-performance PA6 grade for film extrusion processes. Medium viscosity, unreinforced or reinforced Akulon grades are used for various injection molding and blow molding applications. Akulon® Ultraflow® is a high-productivity, high-performance PA6 family for molding processes. Key applications for Akulon: Automotive: Intake manifold, Engine, Powertrain, Airbag containers, Exterior trim, Interior trim, Electrical components and connectors Consumer durables: Power tools, Lawn and garden tools, Small appliances, Sports and leisure equipment, Furniture, Industrial Goods, Transportation E&E: Low voltage switch gear/power distribution, Lighting, Power connectors Film: Specialty and barrier films Information provided by DSM.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Akulon-K223-KMV6-GREY-Nylon-6-30-Mineral-Reinforced-European-and-Asian-Grade-Cond.php

Physical Properties	Metric	English	Comments
Density	1.53 g/cc	0.0553 lb/in ³	(DAM); ISO 1183
Water Absorption	6.2 %	6.2 %	DAM; Sim. to ISO 62
Moisture Absorption at Equilibrium	1.7 %	1.7 %	Humidity Absorption (DAM); Sim. to ISO 62

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	40.0 MPa	5800 psi	ISO 527-1/-2
Elongation at Break	4.0 %	4.0 %	ISO 527-1/-2
Tensile Modulus	3.50 GPa	508 ksi	ISO 527-1/-2
Charpy Impact Unnotched	3.50 J/cm ²	16.7 ft-lb/in ²	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	6.00 J/cm ²	28.6 ft-lb/in ²	ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.500 J/cm ²	2.38 ft-lb/in ²	ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.500 J/cm ²	2.38 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	10°C/min (DAM); ISO 11357-1/-3
UL RTI, Electrical	140 °C	284 °F	UL746B
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	140 °C	284 °F	UL746B
	@Thickness 3.00 mm	@Thickness 0.118 in	
UL RTI, Mechanical with Impact	110 °C	230 °F	UL746B
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	110 °C	230 °F	UL746B
	@Thickness 3.00 mm	@Thickness 0.118 in	
UL RTI, Mechanical without Impact	140 °C	284 °F	UL746B
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	140 °C	284 °F	UL746B
	@Thickness 3.00 mm	@Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	IEC 60093
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	IEC 60093
Dielectric Constant	3.7	3.7	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	10	10	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	25.0 kV/mm	635 kV/in	IEC 60243-1
Dissipation Factor	0.090	0.090	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	0.30	0.30	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Comparative Tracking Index	250 - 399 V	250 - 399 V	PLC 2; UL 746A
	375 V	375 V	

Descriptive Properties	Value	Comments
------------------------	-------	----------

Descriptive Properties	Value	Comments
Flame Retarding Agent	Yes	
Heat stabilized or stable to heat	Yes	
Injection molding	Yes	
Release Agent	Yes	
With Fillers	Yes	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China