

DSM Akulon® S223-F Nylon 66 (European and Asian Grade) (Dry)

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Unreinforced

Material Notes:

The Akulon® product portfolio is engineered for optimum performance to suit different processing techniques and end use markets. Akulon Nylon 6 is used for extrusion applications including barrier film, stock shapes, convoluted tubes, and monofilament. Akulon XP is a high-productivity, high-performance PA6 grade for film extrusion processes. Medium viscosity, unreinforced or reinforced Akulon grades are used for various injection molding and blow molding applications. Akulon® Ultraflow® is a high-productivity, high-performance PA6 family for molding processes. Key applications for Akulon: Automotive: Intake manifold, Engine, Powertrain, Airbag containers, Exterior trim, Interior trim, Electrical components and connectors Consumer durables: Power tools, Lawn and garden tools, Small appliances, Sports and leisure equipment, Furniture, Industrial Goods, Transportation E&E: Low voltage switch gear/power distribution, Lighting, Power connectors Film: Specialty and barrier films Information provided by DSM.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Akulon-S223-F-Nylon-66-European-and-Asian-Grade-Dry.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	ISO 1183
Water Absorption	9.0 %	9.0 %	Sim. to ISO 62
Moisture Absorption at Equilibrium	2.4 %	2.4 %	Humidity Absorption; Sim. to ISO 62

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	90.0 MPa	13100 psi	ISO 527-1/-2
Elongation at Break	40 %	40 %	ISO 527-1/-2
Elongation at Yield	3.5 %	3.5 %	ISO 527-1/-2
Tensile Modulus	3.40 GPa	493 ksi	ISO 527-1/-2
Charpy Impact Unnotched	NB	NB	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	NB	NB	ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.700 J/cm ²	3.33 ft-lb/in ²	ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.700 J/cm ²	3.33 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	100 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	55.6 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	ISO 11359-1/-2
	@Temperature 20.0 $^\circ\text{C}$	@Temperature 68.0 $^\circ\text{F}$	
CTE, linear, Transverse to Flow	100 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	55.6 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	ISO 11359-1/-2
	@Temperature 20.0 $^\circ\text{C}$	@Temperature 68.0 $^\circ\text{F}$	
Melting Point	260 $^\circ\text{C}$	500 $^\circ\text{F}$	10 $^\circ\text{C}/\text{min}$; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	220 $^\circ\text{C}$	428 $^\circ\text{F}$	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	75.0 $^\circ\text{C}$	167 $^\circ\text{F}$	ISO 75-1/-2
Flammability, UL94	V-2	V-2	IEC 60695-11-10
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	V-2	V-2	IEC 60695-11-10
	@Thickness 3.00 mm	@Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Dielectric Constant	3.0	3.0	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	3.2	3.2	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	25.0 kV/mm	635 kV/in	IEC 60243-1
Dissipation Factor	0.0060	0.0060	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.017	0.017	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	600 V	600 V	IEC 60112

Descriptive Properties	Value	Comments
Injection molding	Yes	
Lubricants	Yes	
Release Agent	Yes	

Without Fillers Descriptive Properties	Yes Value	Comments
---	--------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China