

DSM Akulon® S223-G6 Nylon 66-30% Glass Reinforced (European and Asian Grade) (Dry)

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

Material Notes:

The Akulon® product portfolio is engineered for optimum performance to suit different processing techniques and end use markets. Akulon Nylon 6 is used for extrusion applications including barrier film, stock shapes, convoluted tubes, and monofilament. Akulon XP is a high-productivity, high-performance PA6 grade for film extrusion processes. Medium viscosity, unreinforced or reinforced Akulon grades are used for various injection molding and blow molding applications. Akulon® Ultraflow® is a high-productivity, high-performance PA6 family for molding processes. Key applications for Akulon: Automotive: Intake manifold, Engine, Powertrain, Airbag containers, Exterior trim, Interior trim, Electrical components and connectors Consumer durables: Power tools, Lawn and garden tools, Small appliances, Sports and leisure equipment, Furniture, Industrial Goods, Transportation E&E: Low voltage switch gear/power distribution, Lighting, Power connectors Film: Specialty and barrier films Information provided by DSM.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Akulon-S223-G6-Nylon-66-30-Glass-Reinforced-European-and-Asian-Grade-Dry.php

Physical Properties	Metric	English	Comments
Density	1.36 g/cc	0.0491 lb/in ³	ISO 1183
Water Absorption	6.0 %	6.0 %	Sim. to ISO 62
Moisture Absorption at Equilibrium	1.6 %	1.6 %	Humidity Absorption; Sim. to ISO 62

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	190 MPa	27600 psi	ISO 527-1/-2
Elongation at Break	3.0 %	3.0 %	ISO 527-1/-2
Tensile Modulus	9.50 GPa	1380 ksi	ISO 527-1/-2
Charpy Impact Unnotched	7.00 J/cm ²	33.3 ft-lb/in ²	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	8.00 J/cm ²	38.1 ft-lb/in ²	ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	1.00 J/cm ²	4.76 ft-lb/in ²	ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	1.20 J/cm ²	5.71 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties	20.0 µm/m-°C Metric	11.1 µin/in-°F English	Comments
CTE, linear, Parallel to Flow	@Temperature 20.0 °C	@Temperature 68.0 °F	ISO 11359-1/-2
CTE, linear, Transverse to Flow	70.0 µm/m-°C @Temperature 20.0 °C	38.9 µin/in-°F @Temperature 68.0 °F	ISO 11359-1/-2
Melting Point	260 °C	500 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	260 °C	500 °F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	250 °C	482 °F	ISO 75-1/-2
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	IEC 60695-11-10
	HB @Thickness 3.00 mm	HB @Thickness 0.118 in	IEC 60695-11-10

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Dielectric Constant	3.5 @Frequency 1e+6 Hz	3.5 @Frequency 1e+6 Hz	IEC 60250
	3.8 @Frequency 100 Hz	3.8 @Frequency 100 Hz	IEC 60250
Dielectric Strength	30.0 kV/mm	762 kV/in	IEC 60243-1
Dissipation Factor	0.0090 @Frequency 100 Hz	0.0090 @Frequency 100 Hz	IEC 60250
	0.016 @Frequency 1e+6 Hz	0.016 @Frequency 1e+6 Hz	IEC 60250
Comparative Tracking Index	600 V	600 V	IEC 60112

Descriptive Properties	Value	Comments
Injection molding	Yes	
Release Agent	Yes	
With Fillers	Yes	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China