

## DSM Arnite® AV2 390 PET-50% Glass Reinforced (European Grade)

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , Polyethylene Terephthalate (PET), 50% Glass Reinforced

### Material Notes:

Arnite resins are engineered to provide specific performance in applications where DSM technology can offer value. Arnite Molding resins: Standard Unfilled and Reinforced materials High modulus Flame retardant grades Easy molding FR grades for connectors Toughened unfilled materials for durability High modulus, tight specification for critical auto components Toughened reinforced resins Low outgassing grades for reflector surfaces Arnite extrusion resins: Specialized materials for specific uses PET for medical applications Loose buffer Optical fiber tubing PET for stock shapes Applications Automotive: Connectors, sensors and E&E parts, Exterior fittings, Gear housings and motors, Brake valve bodies Electrical & Electronic: Telecoms and IT connectors, Bobbins, Low voltage Power distribution, E-motor components, Lightings and Lamp fittings Consumer Durables: Small Appliances Other: Optical fiber tubing Information provided by DSM.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DSM-Arnite-AV2-390-PET-50-Glass-Reinforced-European-Grade.php](http://www.lookpolymers.com/polymer_DSM-Arnite-AV2-390-PET-50-Glass-Reinforced-European-Grade.php)

Physical Properties	Metric	English	Comments
Density	1.78 g/cc	0.0643 lb/in <sup>3</sup>	ISO 1183
Water Absorption	0.30 %	0.30 %	Sim. to ISO 62
Moisture Absorption at Equilibrium	0.12 %	0.12 %	Humidity Absorption; Sim. to ISO 62

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	210 MPa	30500 psi	ISO 527-1/-2
Elongation at Break	2.0 %	2.0 %	ISO 527-1/-2
Tensile Modulus	19.0 GPa	2760 ksi	ISO 527-1/-2
Charpy Impact Unnotched	5.50 J/cm <sup>2</sup>	26.2 ft-lb/in <sup>2</sup>	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	5.50 J/cm <sup>2</sup>	26.2 ft-lb/in <sup>2</sup>	ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	1.40 J/cm <sup>2</sup>	6.66 ft-lb/in <sup>2</sup>	ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	1.40 J/cm <sup>2</sup>	6.66 ft-lb/in <sup>2</sup>	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	20.0 µm/m-°C	11.1 µin/in-°F	ISO 11359-1/-2
	@Temperature 20.0 °C	@Temperature 68.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Transverse to Flow	40.0 mm/m-°C @Temperature 20.0 °C	53.0 in/in-°F @Temperature 68.0 °F	ISO 11359-1/-2
Melting Point	255 °C	491 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	255 °C	491 °F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	240 °C	464 °F	ISO 75-1/-2
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	IEC 60695-11-10
	HB @Thickness 0.810 mm	HB @Thickness 0.0319 in	IEC 60695-11-10

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	IEC 60093
Dielectric Constant	3.5 @Frequency 1e+6 Hz	3.5 @Frequency 1e+6 Hz	IEC 60250
	3.8 @Frequency 100 Hz	3.8 @Frequency 100 Hz	IEC 60250
Dissipation Factor	0.0020 @Frequency 100 Hz	0.0020 @Frequency 100 Hz	IEC 60250
	0.011 @Frequency 1e+6 Hz	0.011 @Frequency 1e+6 Hz	IEC 60250
Comparative Tracking Index	250 V	250 V	IEC 60112

Descriptive Properties	Value	Comments
Injection molding	Yes	
Release Agent	Yes	
With Fillers	Yes	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China