

## DSM Arnite® D00 301 PET (European Grade) (discontinued \*\*)

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , Polyethylene Terephthalate (PET), Unreinforced

### Material Notes:

Arnite resins are engineered to provide specific performance in applications where DSM technology can offer value. Arnite Molding resins: Standard Unfilled and Reinforced materials High modulus Flame retardant grades Easy molding FR grades for connectors Toughened unfilled materials for durability High modulus, tight specification for critical auto components Toughened reinforced resins Low outgassing grades for reflector surfaces Arnite extrusion resins: Specialized materials for specific uses PET for medical applications Loose buffer Optical fiber tubing PET for stock shapes Applications Automotive: Connectors, sensors and E&E parts, Exterior fittings, Gear housings and motors, Brake valve bodies Electrical & Electronic: Telecoms and IT connectors, Bobbins, Low voltage Power distribution, E-motor components, Lightings and Lamp fittings Consumer Durables: Small Appliances Other: Optical fiber tubing Information provided by DSM.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DSM-Arnite-D00-301-PET-European-Grade-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_DSM-Arnite-D00-301-PET-European-Grade-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	1.34 g/cc	0.0484 lb/in <sup>3</sup>	ISO 1183
Water Absorption	0.80 %	0.80 %	Sim. to ISO 62
Moisture Absorption at Equilibrium	0.30 %	0.30 %	Humidity Absorption; Sim. to ISO 62

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	60.0 MPa	8700 psi	ISO 527-1/-2
Elongation at Break	>= 50 %	>= 50 %	ISO 527-1/-2
Elongation at Yield	3.5 %	3.5 %	ISO 527-1/-2
Tensile Modulus	2.50 GPa	363 ksi	ISO 527-1/-2
Charpy Impact Unnotched	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	ISO 179/1eU
Charpy Impact, Notched	0.600 J/cm <sup>2</sup> @Temperature 23.0 °C	2.86 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	ISO 179/1eA

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	80.0 µm/m-°C @Temperature 20.0 °C	44.4 µin/in-°F @Temperature 68.0 °F	ISO 11359-1/-2
CTE, linear, Transverse to Flow	80.0 µm/m-°C @Temperature 20.0 °C	44.4 µin/in-°F @Temperature 68.0 °F	ISO 11359-1/-2
Melting Point			10°C/min; ISO 11357-1/-3

Thermal Properties	255 °C Metric	491 °F English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	75.0 °C	167 °F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	70.0 °C	158 °F	ISO 75-1/-2
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	IEC 60695-11-10

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	IEC 60093
Dielectric Constant	3.4 @Frequency 1e+6 Hz	3.4 @Frequency 1e+6 Hz	IEC 60250
	3.7 @Frequency 100 Hz	3.7 @Frequency 100 Hz	IEC 60250
Dielectric Strength	23.0 kV/mm	584 kV/in	IEC 60243-1
Dissipation Factor	0.0030 @Frequency 100 Hz	0.0030 @Frequency 100 Hz	IEC 60250
	0.025 @Frequency 1e+6 Hz	0.025 @Frequency 1e+6 Hz	IEC 60250
Comparative Tracking Index	200 V	200 V	IEC 60112

Descriptive Properties	Value	Comments
Injection molding	Yes	
Other Extrusion	Yes	
Transparent	Yes	
Without Fillers	Yes	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China