

DSM Novamid® 1015GH35 BK37 PA6-GF35

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 40% Glass Fiber Filled

Material Notes:

35% Glass Reinforced, Heat Stabilized, Injection Molding

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Novamid-1015GH35-BK37-PA6-GF35.php

Physical Properties	Metric	English	Comments
Density	1.41 g/cc	0.0509 lb/in ³	dry; ISO 1183
Moisture Absorption	2.30 %	2.30 %	Sim. To ISO 62
Linear Mold Shrinkage, Flow	0.0030 cm/cm	0.0030 in/in	ISO 294-4
Linear Mold Shrinkage, Transverse	0.010 cm/cm	0.010 in/in	ISO 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	120 MPa	17400 psi	cond; ISO 527-1/-2
	190 MPa	27600 psi	dry; ISO 527-1/-2
Elongation at Break	2.6 %	2.6 %	dry; ISO 527-1/-2
	6.0 %	6.0 %	cond; ISO 527-1/-2
Tensile Modulus	6.30 GPa	914 ksi	cond; ISO 527-1/-2
	11.4 GPa	1650 ksi	dry; ISO 527-1/-2
Flexural Strength	195 MPa	28300 psi	cond; ISO 178
	295 MPa	42800 psi	dry; ISO 178
Flexural Modulus	6.60 GPa	957 ksi	cond; ISO 178
	9.80 GPa	1420 ksi	dry; ISO 178
Charpy Impact Unnotched	9.60 J/cm ²	45.7 ft-lb/in ²	dry; ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact Unnotched	10.8 J/cm ²	51.4 ft-lb/in ²	cond; ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	1.40 J/cm ²	6.66 ft-lb/in ²	dry; ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	2.40 J/cm ²	11.4 ft-lb/in ²	

Mechanical Properties	Metric @ Temperature 23.0 °C	English @ Temperature 73.4 °F	cond: ISO 179/1eA Comments
-----------------------	---------------------------------	----------------------------------	-------------------------------

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	220 °C	428 °F	dry; ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	206 °C	403 °F	dry; ISO 75-1/-2
Flammability, UL94	HB @Thickness 0.800 mm	HB @Thickness 0.0315 in	dry; IEC 60695-11-10

Electrical Properties	Metric	English	Comments
Volume Resistivity	7.00e+14 ohm-cm	7.00e+14 ohm-cm	dry; IEC 60093
Surface Resistance	3.00e+13 ohm	3.00e+13 ohm	cond; IEC 60093
Dielectric Constant	4.0 @Frequency 100 Hz	4.0 @Frequency 100 Hz	dry; IEC 60250
	4.0 @Frequency 1.00e+6 Hz	4.0 @Frequency 1.00e+6 Hz	dry; IEC 60250
Dielectric Strength	23.0 kV/mm	584 kV/in	dry; IEC 60243-1
Dissipation Factor	0.011 @Frequency 100 Hz	0.011 @Frequency 100 Hz	dry; IEC 60250
	0.019 @Frequency 1.00e+6 Hz	0.019 @Frequency 1.00e+6 Hz	dry; IEC 60250
Comparative Tracking Index	400 V	400 V	dry; IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China