

DSM Stanyl® TE250F9 (COND) Nylon 46 45% Glass Reinforced, Heat Stabilized, Flame Retardant (North America)

Category : Polymer , Thermoplastic , Nylon , Nylon 46 , Nylon 46, Flame Retarded + Glass Fiber Reinforced

Material Notes:

Information provided by DSM Engineering Plastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Stanyl-TE250F9-COND-Nylon-46-45-Glass-Reinforced-Heat-Stabilized-Flame-Retardant-North-America.php

Physical Properties	Metric	English	Comments
Density	1.82 g/cc	0.0658 lb/in ³	(DAM); ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	130 MPa	18900 psi	ISO 527-1/-2
Elongation at Break	3.0 %	3.0 %	ISO 527-1/-2
Tensile Modulus	12.0 GPa	1740 ksi	ISO 527-1/-2
Charpy Impact Unnotched	7.50 J/cm ²	35.7 ft-lb/in ²	ISO 179/1eU
	5.00 J/cm ² @Temperature -30.0 °C	23.8 ft-lb/in ² @Temperature -22.0 °F	ISO 179/1eU
Charpy Impact, Notched	1.50 J/cm ²	7.14 ft-lb/in ²	ISO 179/1eU
	1.30 J/cm ² @Temperature -30.0 °C	6.19 ft-lb/in ² @Temperature -22.0 °F	ISO 179/1eU

Thermal Properties	Metric	English	Comments
Melting Point	295 °C	563 °F	(DAM); ISO 11357-1/-3

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+8 ohm-cm	1.00e+8 ohm-cm	IEC 60093
Dielectric Strength	20.0 kV/mm	508 kV/in	IEC 60243-1
Comparative Tracking Index	325 V	325 V	IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China