

DSM Stanyl® TW341 Nylon 46 (European and Asian Grade) (Cond)

Category : Polymer , Thermoplastic , Nylon , Nylon 46 , Nylon 46, Unreinforced

Material Notes:

Stanyl is a high performance polyamide providing good performance and value across a broad range of automotive and electronic applications. Stanyl offers: Highest mechanical properties at high temperatures Excellent resistance to wear and low friction Outstanding flow for easy processing and exceptional design freedom Stanyl High Flow grades that match the best flowing LCPs while maintaining a high level of mechanical properties Key Applications: Automotive: Powertrain components, Charge-air coolers, EPS and ETC gears, Motor Sensors, Auto connectors, Chain tensioners E&E: Connectors, Microswitches, Bobbins, Memory modules, Motor components, Industrial, Specialty films and fibers, Consumer appliances Information provided by DSM.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Stanyl-TW341-Nylon-46-European-and-Asian-Grade-Cond.php

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in ³	(DAM); ISO 1183
Water Absorption	13.5 %	13.5 %	DAM; Sim. to ISO 62
Moisture Absorption at Equilibrium	3.7 %	3.7 %	Humidity Absorption (DAM); Sim. to ISO 62
Linear Mold Shrinkage, Flow	0.020 cm/cm	0.020 in/in	DAM; ISO 294-4
	0.020 cm/cm	0.020 in/in	DAM; ISO 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	55.0 MPa	7980 psi	ISO 527-1/-2
Elongation at Break	>= 50 %	>= 50 %	ISO 527-1/-2
Elongation at Yield	20 %	20 %	ISO 527-1/-2
Tensile Modulus	1.00 GPa	145 ksi	ISO 527-1/-2
Charpy Impact Unnotched	NB	NB	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	NB	NB	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	1.20 J/cm ²	5.71 ft-lb/in ²	ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	4.50 J/cm ²	21.4 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Tensile Creep Modulus, 1000 hours Mechanical Properties	500 MPa Metric	72500 psi English	ISO 899-1 Comments
--	-------------------	----------------------	-----------------------

Thermal Properties	Metric	English	Comments
Melting Point	295 °C	563 °F	10°C/min (DAM); ISO 11357-1/-3

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+9 ohm-cm	1.00e+9 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093
Dielectric Constant	4.5	4.5	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	22	22	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	15.0 kV/mm	381 kV/in	IEC 60243-1
Dissipation Factor	0.012	0.012	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	0.087	0.087	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Comparative Tracking Index	400 V	400 V	IEC 60112

Descriptive Properties	Value	Comments
Heat stabilized or stable to heat	Yes	
Injection molding	Yes	
Lubricants	Yes	
Platable	Yes	
Release Agent	Yes	
Without Fillers	Yes	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China