

## DSM Yparex® 8102 E Polyolefin Adhesive Resin (European Grade) (discontinued \*\*)

Category : Polymer , Thermoplastic , Adhesives, Sealants, and Coatings , Polyolefin

### Material Notes:

The Yparex range provides outstanding adhesion for all forms of polyethylene including cross-linked PE to: barrier plastics like EVOH and Polyamidemetals like aluminum, steel and copper. Yparex offers: Rheology tailored for your extrusion process Consistent products regarding flow and melt stability Maintains adhesion to metals up to 95°C The bonding that Yparex provides between polyethylene and the other layers develops in the melt phase and depends on contact time and temperature. Film applications: Multi-layer barrier films for food applications with low oxygen permeation Industrial films with oxygen barrier Multi-layer non-food packaging for improved mechanical properties and puncture resistance Pipe applications: Multi-layer barrier pipes for floor heating, protective pipes for cables etc Multi-layer composite pipes (metal/plastic) for 100% diffusion tight pipes that are corrosion resistant and function up to 95°C Information provided by DSM. Yparex B.V. was spun off from DSM in 2011. This grade was discontinued prior to the spinoff.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DSM-Yparex-8102-E-Polyolefin-Adhesive-Resin-European-Grade-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_DSM-Yparex-8102-E-Polyolefin-Adhesive-Resin-European-Grade-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	0.923 g/cc	0.0333 lb/in <sup>3</sup>	ISO 1183
Melt Flow	2.3 g/10 min @Load 2.16 kg, Temperature 190 °C	2.3 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Thermal Properties	Metric	English	Comments
Melting Point	124 °C	255 °F	10°C/min; ISO 11357-1/-3
Vicat Softening Point	102 °C	216 °F	50°C/h 10N; ISO 306

Descriptive Properties	Value	Comments
Enthalpy of Melting	113	ISO 11357-1/-3
Film Extrusion	Yes	
Other Extrusion	Yes	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China