

## Daikin DAI-EL G-621 Fluoroelastomer Terpolymer, Bisphenol Curable Grade, 71% Fluorine Content

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Offers minimal compression set and excellent sealing. The terpolymer type is able to withstand polarized solvents to realize a wide range of application. Features: General purpose with excellent solvent resistance. Information provided by Daikin Industries.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Daikin-DAI-EL-G-621-Fluoroelastomer-Terpolymer-Bisphenol-Curable-Grade-71-Fluorine-Content.php](http://www.lookpolymers.com/polymer_Daikin-DAI-EL-G-621-Fluoroelastomer-Terpolymer-Bisphenol-Curable-Grade-71-Fluorine-Content.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.92 g/cc	1.92 g/cc	at 25°C
Mooney Viscosity	50 @Temperature 121 °C	50 @Temperature 250 °F	ML 1+10

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	76	76	Peak value, at 25°C
Tensile Strength at Break	16.2 MPa	2350 psi	
Tensile Strength, Yield	3.70 MPa @Strain 100 %	537 psi @Strain 100 %	
Elongation at Break	280 %	280 %	
Tear Strength	19.6 kN/m	112 pli	at 25°C
Compression Set	23 %	23 %	70 hours at 25°C
	18 % @Temperature 100 °C	18 % @Temperature 212 °F	70 hours
	20 % @Temperature 175 °C	20 % @Temperature 347 °F	70 hours
	29 % @Temperature 200 °C	29 % @Temperature 392 °F	70 hours

Thermal Properties	Metric	English	Comments
Minimum Service Temperature, Air	-8.00 °C	17.6 °F	TR test, TR10
	-5.00 °C	23.0 °F	Gehman torsion test, T10

Thermal Properties	-2.00 °C Metric	28.4 °F English	TR test TR70 Comments
	-1.50 °C	29.3 °F	Gehman torsion test, T2
Brittleness Temperature	-15.0 °C	5.00 °F	

  

Processing Properties	Metric	English	Comments
Processing Temperature	170 °C	338 °F	Cure Measuring Temperature
Cure Time	3.50 min	0.0583 hour	Curelastmeter

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China