

## Daikin NEOFロン AP-211SH PFA Semiconductor Grade

Category : Polymer , Thermoplastic , Fluoropolymer , PFA , Polyperfluoroalkoxyethylene, Molded/Extruded

**Material Notes:**

NEOFロン PFA semiconductor grade. Applications: Tubing and injection molded parts requiring high stress crack resistance, etc. Information provided by Daikin Industries.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Daikin-NEOFロン-AP-211SH-PFA-Semiconductor-Grade.php](http://www.lookpolymers.com/polymer_Daikin-NEOFロン-AP-211SH-PFA-Semiconductor-Grade.php)

Physical Properties	Metric	English	Comments
Specific Gravity	2.15 g/cc	2.15 g/cc	at 25°C
Bulk Density	1.20 g/cc	0.0434 lb/in <sup>3</sup>	
Melt Flow	10 - 18 g/10 min @Load 5.00 kg, Temperature 372 °C	10 - 18 g/10 min @Load 11.0 lb, Temperature 702 °F	

Mechanical Properties	Metric	English	Comments
Coefficient of Friction	0.040 - 0.060	0.040 - 0.060	
Taber Abrasion, mg/1000 Cycles	<= 96.75	<= 96.75	9.8 N load, cs-10 wheel

Thermal Properties	Metric	English	Comments
Flammability, UL94	V-0	V-0	
Oxygen Index	>= 95 %	>= 95 %	

Electrical Properties	Metric	English	Comments
Dielectric Constant	1.92 - 2.12	1.92 - 2.12	ASTM D150
	@Frequency 1000 Hz	@Frequency 1000 Hz	
Dissipation Factor	1.92 - 2.12	1.92 - 2.12	ASTM D150
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dissipation Factor	0.00010 - 0.00021	0.00010 - 0.00021	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China