

Denka TE-30 Transparent Resin Polymer (MABS resin) ABS

Category : Polymer , Thermoplastic , ABS Polymer

Material Notes:

"TX Polymer" (methyl methacrylate styrene), MS resins as an alternative to acrylic resins, with low density, low moisture absorption, and good moldability, "TH Polymer/TP Polymer," MBS resins with a good balance of transparency, strength and fluidity (methyl methacrylate butadiene styrene), "TE Series/CL Series," transparent ABS resins with excellent color attributes and tensile strength are available (among others). Applications TX is used for: flat display substrates optical components miscellaneous goods. TP/TH are used for: food package sheeting as well as in manufacturing electronic equipment and components miscellaneous goods TE/CL are for: electronic equipment and components information equipment components AV equipment, etc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Denka-TE-30-Transparent-Resin-Polymer-MABS-resin-ABS.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.08 g/cc	1.08 g/cc	ASTM D792
Density	1.079 g/cc	0.03898 lb/in ³	ISO 1183
Melt Flow	2.4 g/10 min	2.4 g/10 min	ISO 1133
	@Load 5.00 kg, Temperature 200 °C	@Load 11.0 lb, Temperature 392 °F	
	23 g/10 min	23 g/10 min	ISO 1133
	@Load 10.0 kg, Temperature 220 °C	@Load 22.0 lb, Temperature 428 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	42	42	ISO 2039-2
Tensile Strength at Break	28.0 MPa	4060 psi	50mm/min; ISO 527-2
	32.0 MPa	4640 psi	
Elongation at Break	50 %	50 %	50mm/min; ISO 527-2
Tensile Modulus	3.90 GPa	566 ksi	50mm/min; ISO 527-1
Flexural Strength	60.0 MPa	8700 psi	ISO 178
Flexural Modulus	1.80 GPa	261 ksi	2mm/min; ISO 178
Charpy Impact, Notched	1.90 J/cm ²	9.04 ft-lb/in ²	ISO 179-2

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	69.0 °C	156 °F	ISO 75-2

Thermal Properties	Metric	English	Comments
Vicat Softening Point	86.0 °C	187 °F	50N; ISO 306
Flammability, UL94	HB	HB	

Optical Properties	Metric	English	Comments
Haze	2.4 % @Thickness 2.00 mm	2.4 % @Thickness 0.0787 in	ISO 14782
Transmission, Visible	91 % @Thickness 2.00 mm	91 % @Thickness 0.0787 in	ISO 13468-1

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China