

Denka TP-801 Transparent Resin Polymer (MBS resin) Polymethacrylate Butadiene Styrene

Category : Polymer , Thermoplastic , Styrene-Butadiene

Material Notes:

"TX Polymer" (methyl methacrylate styrene), MS resins as an alternative to acrylic resins, with low density, low moisture absorption, and good moldability, "TH Polymer/TP Polymer," MBS resins with a good balance of transparency, strength and fluidity (methyl methacrylate butadiene styrene), "TE Series/CL Series," transparent ABS resins with excellent color attributes and tensile strength are available (among others). Applications TX is used for: flat display substrates optical components miscellaneous goods. TP/TH are used for: food package sheeting as well as in manufacturing electronic equipment and components miscellaneous goods TE/CL are for: electronic equipment and components information equipment components AV equipment, etc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Denka-TP-801-Transparent-Resin-Polymer-MBS-resin-Polymethacrylate-Butadiene-Styrene.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.10 g/cc	1.10 g/cc	ASTM D792
Density	1.086 g/cc	0.03923 lb/in ³	ISO 1183
Melt Flow	5.5 g/10 min	5.5 g/10 min	ISO 1133
	@Load 5.00 kg, Temperature 200 °C	@Load 11.0 lb, Temperature 392 °F	
	79 g/10 min	79 g/10 min	ISO 1133
	@Load 10.0 kg, Temperature 220 °C	@Load 22.0 lb, Temperature 428 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	34	34	ISO 2039-2
Tensile Strength at Break	35.0 MPa	5080 psi	50mm/min; ISO 527-2
	42.0 MPa	6090 psi	50mm/min; ASTM D638
Elongation at Break	30 %	30 %	50mm/min; ISO 527-2
Tensile Modulus	4.70 GPa	682 ksi	50mm/min; ISO 527-1
Flexural Strength	68.0 MPa	9860 psi	ISO 178
	69.0 MPa	10000 psi	2mm/min; ASTM D790
Flexural Modulus	2.18 GPa	316 ksi	2mm/min; ASTM D790
	2.20 GPa	319 ksi	2mm/min; ISO 178
Izod Impact Resistance	10.5 J/cm ²	50.0 ft-lb/in ²	

Mechanical Properties	Metric	English	Comments
Charpy Impact, Notched	1.00 J/cm ²	4.74 ft ² -lb/in ²	ISO 179-2

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	64.0 °C	147 °F	ISO 75-2
	72.0 °C	162 °F	ASTM D648
Vicat Softening Point	85.0 °C	185 °F	50N; ISO 306
Flammability, UL94	HB	HB	

Optical Properties	Metric	English	Comments
Haze	2.5 % @Thickness 2.00 mm	2.5 % @Thickness 0.0787 in	ISO 14782
Transmission, Visible	91 % @Thickness 2.00 mm	91 % @Thickness 0.0787 in	ISO 13468-1

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China