

Diamond Polymers DIAMALLOY 1001 CF30 30% Carbon Fiber Filled ABS

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), 30% Carbon Fiber Filled

Material Notes:

Information Provided by Diamond Polymers, Inc. & Network Polymers, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Diamond-Polymers-DIAMALLOY-1001-CF30-30-Carbon-Fiber-Filled-ABS.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.19 g/cc	1.19 g/cc	ASTM D792
Water Absorption	0.14 %	0.14 %	ASTM D570
Linear Mold Shrinkage	0.0010 - 0.0020 cm/cm	0.0010 - 0.0020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	131 MPa	19000 psi	chs 2.0 in/min; ASTM D638
Elongation at Yield	1.5 %	1.5 %	chs 2.0 in/min; ASTM D638
Flexural Strength	179 MPa	26000 psi	ASTM D790
Flexural Modulus	16.536 GPa @Thickness 3.17 mm	2398.3 ksi @Thickness 0.125 in	chs 0.05 in/min; ASTM D790
Izod Impact, Notched	0.587 J/cm @Thickness 3.17 mm	1.10 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	104 °C	219 °F	0.125";; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	100 ohm-cm	100 ohm-cm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China

