

Diamond Polymers Softflex® SF 8900

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

Information Provided by Diamond Polymers, Inc. & Network Polymers, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Diamond-Polymers-Softflex-SF-8900.php

Physical Properties	Metric	English	Comments
Density	0.990 g/cc	0.0358 lb/in ³	ASTM D792
Melt Flow	17.5 g/10 min	17.5 g/10 min	ASTM D1238
	@Load 1.00 kg, Temperature 235 °C	@Load 2.20 lb, Temperature 455 °F	
	33.4 g/10 min	33.4 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 200 °C	@Load 11.0 lb, Temperature 392 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40 - 50	40 - 50	ASTM D792
Tensile Strength, Yield	5.50 MPa	798 psi	chs 20 in/min; ASTM D638
Elongation at Break	530 %	530 %	chs 20 in/min; ASTM D412
Tear Strength	28.0 kN/m	160 pli	ASTM D624

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China