

## Domo Domamid® 32 Polyamide 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

**Material Notes:**

DOMAMID® 32 are Polyamide 6 pellets with a higher viscosity produced from Caprolactam by polymerization. Applications: Standard quality for production of monofilaments and fishing nets. Information provided by Domo

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Domo-Domamid-32-Polyamide-6.php](http://www.lookpolymers.com/polymer_Domo-Domamid-32-Polyamide-6.php)

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in <sup>3</sup>	
Volatiles	<= 0.60 %	<= 0.60 %	Extractables; BUP - 06
Apparent Bulk Density	0.600 - 0.800 g/cc	0.0217 - 0.0289 lb/in <sup>3</sup>	
Viscosity Measurement	3.15 - 3.25 @Temperature 20.0 °C	3.15 - 3.25 @Temperature 68.0 °F	1% Solution in 96% H2SO4; BUP - 02

Thermal Properties	Metric	English	Comments
Melting Point	221 °C	430 °F	

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.060 %	<= 0.060 %	BUP - 05

Descriptive Properties	Value	Comments
Chip Number	ca. 80 to 100/g	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China