

Dow AMPLIFY™ GR 205 Maleic anhydride grafted (MAH) polymer

Category : Polymer , Thermoplastic

Material Notes:

AMPLIFY™ GR 205 Functional Polymer is designed as a blend component for unmodified polyethylene. In tie layers for flexible packaging, it promotes adhesion of polyethylene to barrier polymers such as polyamide and ethylene vinyl alcohol (EVOH). The functionality of this polymer also promotes adhesion between metal, polyolefins, cellulose, polyester, polycarbonate, glass, and foil. Information provided by

Dow

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-AMPLIFY-GR-205-Maleic-anhydride-grafted-MAH-polymer.php

Physical Properties	Metric	English	Comments
Density	0.962 g/cc	0.0348 lb/in ³	ASTM D792
Filler Content	>= 1.0 %	>= 1.0 %	MAH graft; Dow Method
Melt Flow	2.0 g/10 min @Load 2.16 kg, Temperature 190 °C	2.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China