

Dow AMPLIFY™ GR 208 Maleic anhydride grafted (MAH) polymer

Category : Polymer , Thermoplastic

Material Notes:

AMPLIFY™ GR 208 Functional Polymer is a post reactor maleic anhydride grafted (MAH) polymer. The base polymer is an ethylene-butene copolymer exhibiting high flexibility and elasticity. It can be utilized in monolayer and coextruded films and in blends with other polyolefins to enhance toughness of the structure. This product is a low gel MAH-grafted elastomer useful to improve impact resistance for polyamide or other engineering resins and to enhance interlayer adhesion in co-extruded films. Information provided by Dow

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-AMPLIFY-GR-208-Maleic-anhydride-grafted-MAH-polymer.php

Physical Properties	Metric	English	Comments
Density	0.8985 g/cc	0.03246 lb/in ³	ASTM D792
Filler Content	0.25 - 0.50 %	0.25 - 0.50 %	MAH graft; Dow Method
Melt Flow	3.3 g/10 min @Load 2.16 kg, Temperature 190 °C	3.3 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	90	90	5 sec; ASTM D2240
	91	91	1 sec; ASTM D2240
Tensile Strength, Ultimate	11.0 MPa	1600 psi	ASTM D638
Elongation at Break	900 %	900 %	ASTM D638
Flexural Modulus	0.103 GPa	15.0 ksi	2% Secant; ASTM D790

Thermal Properties	Metric	English	Comments
Melting Point	117 °C	243 °F	Dow Method
Glass Transition Temp, Tg	-47.0 °C	-52.6 °F	Dow Method

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China