

## Dow ASPUN™ 6811A Linear Low-Density Polyethylene (LLDPE)

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE

### Material Notes:

ASPUN™ 6811A Fiber Grade Resin: Suggested Optimum Process: Spun Bond Typical Application: Non-woven Fabrics Information provided by Dow

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Dow-ASPUN-6811A-Linear-Low-Density-Polyethylene-LLDPE.php](http://www.lookpolymers.com/polymer_Dow-ASPUN-6811A-Linear-Low-Density-Polyethylene-LLDPE.php)

Physical Properties	Metric	English	Comments
Density	0.941 g/cc	0.0340 lb/in <sup>3</sup>	ASTM D792
Melt Flow	27 g/10 min @Load 2.16 kg, Temperature 190 °C	27 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Thermal Properties	Metric	English	Comments
Melting Point	125 °C	257 °F	Dow Method (DSC)

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China