

Dow C719-35RNHP Polypropylene Resin

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

DOW C719-35RNHP is intended for use in injection molding applications requiring a good impact/stiffness balance. Information provided by DowDow Announced Sale of Global Polypropylene Business to Braskem in July 2011.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-C719-35RNHP-Polypropylene-Resin.php

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in ³	ASTM D792
Melt Flow	35 g/10 min @Temperature 230 °C	35 g/10 min @Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	20.7 MPa	3000 psi	molded and tested in accordance with ASTM D 4101; ASTM D638
Elongation at Yield	5.0 %	5.0 %	molded and tested in accordance with ASTM D 4101; ASTM D638
Flexural Modulus	1.07 GPa	155 ksi	1% Secant; molded and tested in accordance with ASTM D 4101; ASTM D790A
Izod Impact, Notched	1.87 J/cm	3.50 ft-lb/in	molded and tested in accordance with ASTM D 4101; ASTM D256A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	95.0 °C	203 °F	unannealed; molded and tested in accordance with ASTM D 4101; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China