

Dow Corning 236 DISPERSION

Category : Polymer , Thermoset , Silicone

Material Notes:

Flowable (as supplied) silicone RTV coating Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-236-DISPERSION.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.64 g/cc	1.64 g/cc	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Solids Content	70 %	70 %	
Viscosity	675 cP	675 cP	dynamic

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	20	20	
Tensile Strength, Ultimate	2.24 MPa	325 psi	
Elongation at Break	500 %	500 %	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	150 °C	302 °F	
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	
Flash Point	>= 10.0 °C	>= 50.0 °F	closed cup

Processing Properties	Metric	English	Comments
Cure Time	1440 min	24.0 hour	
	@Temperature 22.0 °C	@Temperature 71.6 °F	
Shelf Life	12.0 Month	12.0 Month	

Descriptive Properties	Value	Comments
Color	white	
Flowable	yes	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China