

Dow Corning 3629

Category : Polymer , Thermoset , Silicone

Material Notes:

Two Part LSR System Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-3629.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.144 g/cc	1.144 g/cc	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Viscosity	8000 cP	8000 cP	dynamic

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	27	27	
Tensile Strength, Ultimate	1.300 MPa	188.5 psi	
Elongation at Break	275 %	275 %	

Processing Properties	Metric	English	Comments
Shelf Life	12.0 Month	12.0 Month	

Descriptive Properties	Value	Comments
Color	white	
Mix Ratio (X:1)	10	Base to Catalyst ETN

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China