

## Dow Corning SILASTIC® LC-20-2004 PART A&B KIT

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

### Material Notes:

20 Durometer, 2 parts, 1 to 1 mix, translucent, FDA 21 CFR 177.2600 and BfR, XV, molding and injection molding grade Liquid Silicone Rubber. Fast curing speed, long pot life (72 hours), high transparency, high tear strength, low compression set. Information provided by Dow Corning

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Dow-Corning-SILASTIC-LC-20-2004-PART-AB-KIT.php](http://www.lookpolymers.com/polymer_Dow-Corning-SILASTIC-LC-20-2004-PART-AB-KIT.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	23	23	
Tensile Strength, Ultimate	7.143 MPa	1036 psi	
Elongation at Break	978 %	978 %	
Tear Strength	22.6 kN/m	129 pli	
Compression Set	21.3 %	21.3 %	

Processing Properties	Metric	English	Comments
Shelf Life	6.00 Month	6.00 Month	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China